



FUJIAN JIALONG ADHESIVE TAPE CO., LTD.

NO.11 XIAZHAI ROAD, JIULONG INDUSTRY PARK, HUA AN ECONOMIC DEVELOPMENT ZONE, HUA AN COUNTY,
ZHANGZHOU CITY, FUJIAN 363000 CHINA Tel:+86-596-728-0001 Fax:+86-596-728-0003 <http://www.jl3tape.com/>

JLN-1440 (Tan)

PRODUCT DESCRIPTION

JLN-1440 flatback packaging tape is a quick, sure sealing, economical, pressure-sensitive flatback tape which can increase packaging line efficiency. It is versatile and offers a positive attractive seal which matches most corrugated cardboard. It's quick stick and has excellent adhesion which discourages pilfering. It can be used on all types of cartons.

PERFORMANCE FEATURES

With high adhesion and high tensile strength, can tolerate the high temperature and low temperature, easy tear, not deformed, non-polluting, recyclable, environment friendly.

STORAGE CONDITION

It's recommended to store in clean and dry place. Damaged packaging shall be prevented. Not stored with volatile solvent. The temperature of storage shall be 4 to 26 °C and the humidity shall be between 40% and 50%. Rotate inventory recommended.

BRANCHES:

SHANGHAI JIALONG FIBER TAPE CO.,LTD.

No.211,Yuxin Rd,Songjiang Dist,Shanghai,China.

JIALONG GROUP PTY LTD.

Unit 83, 79 St Hilliers Road Auburn NSW 2144, Australia.

Non-reinforced sell-adhesive kraft paper tape

Physical Properties	Standard	Metric	Test Method	
Color	Tan			
Adhesive	Synthetic Rubber: 40 g/m²			
Backing	Kraft Paper: 80 g/m²			
Total Thickness	5.1 mils	0.13 mm	ASTM D-3652	GB/T7125
Peel Adhesion 90°	82.7 oz/in	23 N/25mm	ASTM D-3330	GB/T2792
Holding Power	>48 h	>48 h	ASTM D-3654	GB/T4851
Tensile Strength	24.7 lbs/in	110 N/25mm	ASTM D-3759	GB/T7753
Elongation at Break	1.5%	1.5%	ASTM D-3759	GB/T7753
Service Tem.--Mini	23°F	-5°C	BC/BD-220SE	BC/BD-220SE
Service Tem.--Max	158°F	70°C	DHG-9055A	DHG-9055A

Other dimensions available upon request.

The above properties and results obtained refer to the average values of laboratory testing carried out on the samples of JIALONG product. JIALONG does not guarantee testing accuracy and makes no guarantee of product performance, safety, or suitability, either expressed or implied, when used alone or in combination with other products. JIALONG strongly urges users to undertake independent testing in order to verify the suitability of the product for whatever intended use. JIALONG assumes no responsibility for any damage or injury sustained as a result of the use of its products.

